ANRUDA®
Anruda Fitness Fabric

NO.202610263517001
A3517

# SCHEDA TECNICO-COMMERCIALE

# Commercial - Technical Data

Anruda Internal Quality Standard Requirements, Version 2025-A

## Basic test information

| | | | | | |
|---|---|---|---|---|---|
| **Sample Information** | **Card No.:** | 202610263517001 | **Sample Photo** |  | |
| | **Material:** | A3517 | | | |
| | **Color:** | Purple | | | |
| **Type of Test** | Internal Test | **Sample Receipt Date** | 2026.10.24 | **Report Issue Date** | 2026.10.26 |

| Test Item | Test Method | Specification Requirement | Test Result | Assessment |
|---|---|---|---|---|
| **Fibre Content** | ISO 1833-20:2018 | / | 75.6% Nylon<br>24.4% Spandex | **Pass** |
| **Color Fastness to Rubbing** | ISO 105-X12:2016 | Dry ≥ 4<br>Wet ≥ 3-4 | Dry: 4-5<br>Wet: 4-5 | **Pass** |
| **Pilling Resistance** | ISO 12945-2:2020<br>Self-fabric abradant | ≥ 3-4 | 4-5 | **Pass** |
| **Dimensional Change After Washing** | ISO 3759:2011<br>ISO 6330:2021 4N<br>ISO 5077:2007 | (-3.0% ~ +1.0%)<br>(+) indicates extension<br>(-) indicates shrinkage | Lengthwise: -1.5%<br>Widthwise: -0.3% | **Pass** |
| **Formaldehyde Content** | ISO 14184-1:2011 | Not Detected | Not Detected | **Pass** |
| **pH Value** | ISO 3071:2020 | 4.0-7.5 | 7.1 | **Pass** |

Certifications

ISO9001 · OEKO-TEX STANDARD 100 23.HCN.41617 Hohenstein · Global Recycled Standard · MA · CNAS · ILAC-MRA

安切达品质测试专用章
ANRUDA QUALITY TEST SEAL

**Note / Notes:**

**We recommend testing each dyebath before any treatment or application other than cutting and sewing.**

To improve our products, we reserve the right to modify these, as and when necessary.