ANRUDA®
Anruda Fitness Fabric


NO.202610263627004
A3627

# SCHEDA TECNICO-COMMERCIALE

# Commercial - Technical Data

Anruda Internal Quality Standard Requirements, Version 2025-A

**Basic test information**

| | | | | | |
|---|---|---|---|---|---|
| **Sample Information** | **Card No.:** | 202610263627004 | **Sample Photo** |  | |
| | **Material:** | A3627 | | | |
| | **Color:** | Greyish White | | | |
| **Type of Test** | Internal Test | **Sample Receipt Date** | 2026.10.24 | **Report Issue Date** | 2026.10.26 |

| Test Item | Test Method | Specification Requirement | Test Result | Assessment |
|---|---|---|---|---|
| **Fibre Content** | ISO 1833-20:2018<br>ISO 1833-1:2020 | / | 55.7% Polyester<br>37.2% Modal<br>7.1% Spandex | **Pass** |
| **Pilling Resistance** | ISO 12945-2:2020<br>Self-fabric abradant | ≥ 3-4 | 3-4 | **Pass** |
| **Dimensional Change After Washing** | ISO 3759:2011<br>ISO 6330:2021 4N<br>ISO 5077:2007 | (-3.0% ~ +1.0%)<br>(+) indicates extension<br>(-) indicates shrinkage | Lengthwise: -2.0%<br>Widthwise: -0.5% | **Pass** |
| **Formaldehyde Content** | ISO 14184-1:2011 | Not Detected | Not Detected | **Pass** |
| **pH Value** | ISO 3071:2020 | 4.0-7.5 | 7.1 | **Pass** |

Certifications

ISO9001 · OEKO TEX STANDARD 100 23.HCN.41617 Hohenstein · Global Recycled Standard · MA · CNAS · ilac-MRA

东莞市安润达品质测试专用章
ANRUDA
QUALITY TEST SEAL

**Note / Notes:**

**We recommend testing each dyebath before any treatment or application other than cutting and sewing.**

To improve our products, we reserve the right to modify these, as and when necessary.